

LUPOY HR5007AC

Injection Molding Grade, PC/ABS

Description

Heat resistance, High flow, High Impact at low Temp.

Application

Automotive Interior, Electric/Electrics

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Specific Gravity		ISO 1183	kg/m ³	1,140
Molding Shrinkage (Flow), 3.2mm		LG Method	%	0.5~0.8
Melt Flow Index	250 °C/2.16kg	ISO 1133	g/10min	4
Melt Flow Index	260 °C/5.0kg	ISO 1133	g/10min	18
Melt Flow Index	300 °C/1.2kg	ISO 1133	g/10min	
Melt Flow Index	300 °C/2.16kg	ISO 1133	g/10min	
Mechanical				
Tensile Modulus		ISO 527		
@ Yield	1mm/min		MPa	
Tensile Strength		ISO 527		
@ Yield	50mm/min		MPa	50
Tensile Strain		ISO 527		
@ Break	50mm/min		%	100
Flexural Strength	2mm/min	ISO 178	MPa	80
Flexural Modulus	2mm/min	ISO 178	MPa	2,200
Charpy Impact Strength		ISO 179		
	23°C		kJ/m ²	
	-30°C		kJ/m ²	
Charpy Impact Strength (Notched)		ISO 179		
	23°C		kJ/m ²	
	-30°C		kJ/m ²	
IZOD Impact Strength, 4.0mm (Notched)		ISO 180		
	23°C		kJ/m ²	46
	-30°C		kJ/m ²	
Thermal				
Heat Deflection Temperature, 6.4mm (Unannealed)		ISO 75		
	1.8MPa		°C	
	0.45MPa		°C	
Vicat Softening Temperature		ISO 306		
	50N, 50 °C/h		°C	131
Flammability		UL94	Thickness	
HB			mm	1.6
V-0			mm	
5VA			mm	
5VB			mm	

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection moulded specimens and after 48 hours storage at 23 °C, 50% relative humidity.

Updated : October-29, 2014

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUPOY HR5007AC

Injection Molding Grade, PC/ABS

Description

Heat resistance, High flow, High Impact at low Temp.

Application

Automotive Interior, Electric/Electrics

Processing Guide (Injection Molding)

Processing Parameters		Unit	Value
Drying Temperature		°C	80 ~ 100
Drying Time		hrs	4 ~ 6
Minimum Moisture Content		%	0.02
Melt Temperature		°C	250 ~ 275
Cylinder Temperature	Rear	°C	240 ~ 270
	Middle	°C	245 ~ 275
	Front	°C	245 ~ 275
Nozzle Temperature		°C	245 ~ 275
Mold Temperature		°C	50 ~ 70
Back Pressure		kg/cm ²	
Screw Speed		rpm	40 ~ 70

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.